

GREEN SYNTHESIS OF SILVER NANOPARTICLES FROM *COUROUPITA GUIANENSIS* AUBL. FLOWER PETAL EXTRACT AND ITS ANTIMICROBIAL ACTIVITY

*Nikhitha K. P¹, Navyashree H. T²

¹Student, Department Of Botany, Bharathi College PG and Research Center, Bharathi Nagar, Karnataka, India.

²Assistant Professor, Department Of Botany, Bharathi College PG and Research Center, Bharathi Nagar, Karnataka, India.

Abstract: Nanoparticles are eco-friendly approach for green synthesis of nanoparticles using natural plant extract is gaining a notable importance now a days. The present study deals with the synthesis of silver nanoparticles using *Couroupita guianensis* Aubl petal extract. The complete reduction of silver ions was observed after 48hrs of reaction at 30°C under shaker condition. The formulation of silver nanoparticles was confirmed by UV-Visible spectroscopy, XRD and SEM analysis. The antifungal activity evaluate against *Aspergillus niger* and *Rhizopus stolonifer*. The antibacterial activity evaluated against *E.coli* and *B.subtilis*.

Key word: Green synthesis, Silver nanoparticles, *C.guianensis*.

I. INTRODUCTION:

Nanoparticles are often referred to as particles with a maximum size of 100nm. Nanoparticles exhibit unique properties, which are quite different than those of large particles (Mohsen *et al.*, 2011). An important area of research in nanotechnology deals with the synthesis of nanoparticles of different chemical compositions, dimension and controlled monodispersity (Swapna *et al.*, 2012). *Couroupita guianensis* Aubl. is belongs to the family Lecythidaceae, and it is a large deciduous tropical tree 90' tall. The leaves, up to 6" long, are simple with serrate margin; it flowers in racemes; the yellow, reddish and pink with stunning fragrant. Flower are large 3" to 5" waxy aromatic smelling growing directly on the bark of the trunk (cauliflory). The cannon ball tree possesses many medicinal properties such as antibiotic, antifungal, antiseptic and analgesic qualities, Juice made from the leaves is used to cure skin diseases and malaria. Young leaves ease toothache (Preetha Devaraj *et al.*, 2013).

II. MATERIALS AND METHODS:

A. Preparation of the Plant Extracts:

Collect the healthy leaves from the selected plant, weigh 20g of leaves and washed thoroughly with distilled water, then it cut into small pieces, the finely cut into pieces were boiled in 100ml of distilled water for 15 to 20 minutes, then cool the solution and filtered using whatmann no 1 filter paper, collect the solution and used for further purposes (Tahira *et al.*, 2018).



Fig 1: AgNO₃ + *C.guianensis* petal extract

- B. Synthesis of Silver Nanoparticles:** Silver nitrate was used as a precursor in synthesis of silver nanoparticles, 5ml of leaf extract was added to 100ml of 1mM AgNO₃ (99.99%) aqueous solution in a conical flask at room temperature. The flask were put in shaker at 30°C and reaction was carried out for a period of 48 hrs (Swapna *et al.*, 2012).
- C. UV-Visible Spectral Analysis:** The gradual change in the colour of a sample from light green to dark brown colour was observed and the bio-reduction of silver ions in the solvent extracts was monitored by periodic evaluation of the suspension (2ml) after incubation of 48hrs under dark condition, the aliquotes were subsequently measured for the UV-visible spectral by scanning in the region from 200-800nm.
- D. SEM Analysis:** SEM analysis was undertaken to know the size and shape of the silver nanoparticles biosynthesis using the plant. The analysis was done

using Noran system 7, S-3400N model. Thin films of the samples were prepared on tungsten filament by dropping a very small amount of the samples on the grid, extra solution was removed using a blotting paper. Thin film on the SEM grid was allowed to dry and the images of nanoparticles were taken.

- E. XRD Analysis:** In XRD analysis the samples were drop-coated onto copper plate by just dropping a small amount of sample on the plate frequently allowed to dry and finally thick coat of sample was prepared the XRD measurements were performed in a Rigako model with step size 0.02 and an angle of 60°-70°. The particles size of the prepared samples were determined by using Scherrer's equation as follows:

$$D = \frac{k\lambda}{\beta \cos\theta}$$

Where D is the crystal size, λ is the wave length of x-ray, θ is the Bragg's angle in radians and β is the full width at half maximum of the peak in radians, k is constant.

- F. Antibacterial Assay:** Antibacterial assay was studied using disc diffusion method. Nutrient agar media was prepared, and pour into sterile petriplate and allowed to solidify, using sterile cotton swab fresh bacterial culture were spread over the plate followed by spread plate technique, filter paper discs saturated with AgNO₃+plant extract. Antibiotics (+ve control) and filter paper disc with water (-ve control) were placed on to the plates with the help of forceps. Incubated at 37°C. Growth zones were read only after 24hrs, zone of inhibition was calculated.


- G. Antifungal assay:** Antifungal activity was tested by well diffusion method. Aqueous extract of two AgNO₃ samples were tested against. The PDA media was poured into sterile petriplates and allowed to solidify, then using sterile cotton swab fresh fungal culture were spread over the plate by spread plate technique. 5mm well made on PDA media using a sterile disc. Wells were filled with AgNO₃ plant extract. Antibiotic (+ve control), distilled water (-ve control) is separate well. The plate was incubated at 25°C for 48-72hrs, after incubation zone of inhibition was calculated.

III. RESULTS:


Observation: After 48 hrs, distinct change in the colour of experimental sample was observed. The colour of experimental sample turned from light green to dark brown colour. The brown colour confirms that the colour change is due to reduction of silver ions which indicates the formation of Ag nanoparticles.

UV-Vis Spectroscopy: The confirmation, formation and stability of synthesized silver ion nanoparticles was confirmed by UV-Vis spectrum. It was recorded by using AgNPs and bioreduction of Ag⁺ ion was also monitored in the UV-Vis spectrophotometer. The surface plasmon resonance bands are influenced by size, shape, morphology, composition and dielectric environment of prepared NPs. 2ml of synthesized AgNPs solution of *Couroupita guianensis* Aubl. were observed before and after the incubation and the UV ranges between 200-800nm.

Before incubation, the synthesized AgNPs shows peaks at 435 nm of *Couroupita guianensis* Aubl. respectively. After the incubation period of 48 hrs the synthesized AgNPs showed broad surface plasmon resonance at 461nm of *Couroupita guianensis* Aubl. respectively.



Graph 1: (a) UV-spectra of *Couroupita* petal extract before incubation



Graph 1: (b) UV – Spectra of after incubation

Scanning Electron Microscope Analysis: SEM analysis of the silver nanoparticles solution were clearly distinguishable owing to their size difference. The SEM images show the AgNPs synthesized from *Couroupita guianensis* Aubl. extract which further confirms the presence of AgNPs. The shape of the AgNPs in

Couroupita extracts was spherical and size of AgNPs is 6.2 nm as confirmed by SEM images.





Fig. 2: SEM image of *Couroupita guianensis* silver nanoparticle

XRD Analysis: X-ray Diffraction studies of two samples show different diffraction peaks. *Couroupita guianensis* Aubl. Plant extract shows 37.97°, 65.06°, 77.71°. 2 theta values and crystalline planes of Ag sample.

The average size of the AgNPs formed in bio-reduction process is determined by using $D = \frac{k\lambda}{\beta \cos\theta}$ and it is estimated that average size of *C.guianensis* Aubl. 877.48, 984.15 and 1065.49 shows the XRD pattern of the silver nanoparticles formed in our experiment.



Graph 2: XRD result of *Couroupita guianensis* Abul. silver nanoparticles

Table 1: A table show XRD result of *Couroupita guianensis* Aubl. Silver nanoparticles

d-spacing	2-theta	H	K	L	Average size
2.367	37.977	1	0	1	877.48
1.432	65.062	1	0	1	984.15
1.227	77.71	1	0	1	1065.49

Antimicrobial Analysis: Toxicity studies on pathogen opens a door for Nanotechnology applications in medicine. Biological synthesis of metal NPs is a traditional method and the use of a plant extract as a new awareness for the control of disease, besides being safe and no phyto-toxic effects. The biologically synthesized AgNPs using *Couroupita guianensis* Abul. And *Alternanthera pungens* kunth. were found to be highly toxic against different pathogenic bacteria and fungi of selected species. The AgNPs against followed by *E.coli*

(Gram positive), *Bacillus* (Gram negative), Antifungal activity was observed against *A.niger* and *R.stolifer*.

The use of plant extract is effective against various micro-organisms including plant pathogens. Oligodynamic silver antimicrobial efficiency extends well beyond its vitrototoxicity. The ionic silver strongly interacts with thiol groups of vital enzymes and in activate the vital activity. Experimental evidence indicate that DNA losses its replication ability, once the attributed their stability in the medium as a colloid, which modulates the phosphotyrosine profile of the pathogen proteins and arrests its growth, the growth of micro-organisms was inhibited by the synthesized AgNPs showed variation in the inhibition if growth of micro-organisms may be due to the presence of peptide-glycin, which is a complex structure and after contains teichoic acids or lilitochoic acids which have a strong negative charge. This charge may contribute to the sequestration of free silver ions. Thus gram positive bacteria may allow less silver to reach the cytoplasmic membrane than the gram negative bacteria.





Fig. 3

Antibacterial activity of AgNPs of *Couroupita guianensis* Aubl against to selected bacterial culture by disc diffusion method.

- a) Positive control - Ampicillin
- b) AgNPs solution - *Couroupita guianensis* Aubl.
- c) Negative control - Water

Table 2: The table shows antibacterial activity of AgNPs of *Couroupita guianensis* Aubl. against selected bacterial culture.

Plant used	Bacterial culture	Diameter of inhibition zone of bacteria (in mm)		
		-ve control	AgNPs	+ve control
<i>Couroupita guianensis</i> Aubl	<i>Escherichia coli</i>	-	1.0±0.1	-
	<i>Bacillus subtilis</i>	-	2.0±0.1	-



Graph 3: Graphical representation of antibacterial activity against AgNPs of *Couroupita guianensis* Aubl.





Fig. 4

Antifungal activity of AgNPs of *Couroupita guianensis* Aubl. Against to selected fungal culture by well method.

- a. Positive control - Ampoxin
- b. AgNPs solution - *Couroupita guianensis* Aubl
- c. Negative control - Water

Table 3: A table shows Antifungal activity of AgNPs of *Couroupita guianensis* Aubl. against selected fungal culture.

Plants used	Fungal culture	Diameter of Inhibition zone of Fungal (in mm)		
		-ve control	AgNPs	+ve control
<i>Couroupita guianensis</i> Aubl	<i>Rhizopus stolonifer</i>	2±0.1	3±0.2	2±0.1
	<i>Aspergillus niger</i>	1±0.1	10±0.3	2±0.1



Graph 4: Graphical representation of Antifungal activity against AgNPs of *Couroupita guianensis* Aubl.

IV. CONCLUSION:

The current investigation demonstrated that the aqueous extract of *Couroupita guianensis* petal showed noticeable antibacterial potential and was also capable of producing AgNPs extract, cellularly, furthermore the biosynthesized practices had on excellent antibacterial activity against some gram +ve and gram -ve bacteria. Nanoparticle well definitely pave way towards minimizing the utilization of this multipurpose nanotechnology.

Acknowledgement:

Department of Botany, Bharathi college PG and Research center and Bharathi college of Pharmacy.

REFERENCES:

- Mohsen Zargar, Azizah Abdul Hamid, Fatima Abu Bakar, Mariana Nor Shamusudin, Kamyar Shameli., Fatemeh Jahanshiri and Farah Farahani., 2011. *Green synthesis and antibacterial effect of silver nanoparticles using Vitex negundo L.* Molecules, vol. (26); 6667-6676.
- Preetha Devaraj, Prachi Kumari, Chirom Aarti and Arun Renganathan., 2013. *Synthesis and characterization of silver nanoparticles using Cannonball leaves and their cytotoxic activity against MCF-7 cell line.* Hindawi Publishing Corporation Journal of Nanotechnology.
- Swapna Alex, Preetha Rani M.R, Soni K.B, Deepa S.Nair and B.R. Reghunath., 2012. *Biosynthesis of silver nanoparticles with antibacterial activity using leaf extract of Michelia champaca.* Jour Pl Sci Res, vol 28(iss.1); 121-126.
- Tahira Akther, Mohd Shahanbaj Khan, Hemalatha Srinivasan., 2018. *Novel silver nanoparticles synthesized from anthers of Couroupita guianensis Abul. Control growth and biofilm formation in human pathogenic bacteria.* Nano Biomed. Eng, vol. 10 (Iss. 3); 250-257.